

EFS-707

EFS-707 Epoxy Filler Surfacer is a 100% solids, three component, epoxy patching compound formulated to repair concrete cracks, bug holes and imperfections. May be applied one inch thick to a vertical surface without slumping, cracking or shrinking. For thicker applications use multiple applications.

EFS-707 Epoxy Filler Surfacer consists of three components, two liquid and one dry. Available in kit sizes of one quart and one gallon. The blend ratio for the two liquid components is 1:1 by volume. The dry portion can be added in a quantity that will produce the desired viscosity of the mixture.

Apply EFS-707 to a clean, dry surface free from any contaminants including loose masonry, dust, dirt, rust, grease, oil, etc. which will interfere with adhesion. Concrete must be cured for a minimum of 28 days. Type II high early concrete and steam cured concrete may be worked when the moisture content is below 14% surface moisture.

Mixing of EFS-707 can be accomplished by first blending the two liquid portions together. Blend thoroughly by using a mechanical mixer. Add the desired amount of Part C aggregate to the Part A and Part B mixture while under agitation. After mixing, the pot life is 45 minutes @90F, one hour at 70°F, and 2 hours @ 50F. If less than a complete kit is required, always keep packaged ratios consistent. For example, to mix one half the packaged kit, blend one-half the two liquids together and half the dry portion etc.

Apply by putty knife or trowel. Use a small amount of solvent to lubricate the putty knife or trowel. Allow to cure overnight between applications and before coating or painting. Do not apply if the substrate or ambient air temperature is below 40°F.

**FILLS UP TO A ONE-INCH
CONCRETE CRACK.
TROWELABLE.**

**EASY TO MIX.
EASY TO APPLY.**

**NO SHRINK.
100% SOLIDS.**

LOW ODOR

**RESISTS ATTACK FROM HARSH
CHEMICALS, SOLVENTS,
ALKALIS AND ACIDS**